

Stormwaterworks.com, LLC
48 Union Street, Suite M
Stamford, CT 06906-0905
Phone: 203-324-0045 / Fax: 203-324-0075

Temporary Spill Berms



Standard 10 foot sections can be cut to various lengths to meet custom requirements

Unique, urethane material “weeps” into small cracks and crevices to seal off liquid flow.

The spillberm is non-absorbing and is easily cleaned for repeated use.

Also available in black to help hide dirt and grime

Applications include: spill response, temporary containment, sealing off doorways during washdown operations

Due to the nature of softer urethane, the physical properties of these products may change with exposure to certain environmental conditions like temperature, humidity and UV radiation. Regular inspection of the stored product should be done to ensure it is in a usable state.

Temporary Spill Berm Chemical Compatibility Guide – please see key on next page

Chemical	Chemical Class	Swelling (0-2)	Visible Degradation (0-2)	Rating
Acetone	Ketones	2	0	NR
Acetonitrile	Nitriles	1	0	Fair
Aluminum Salts	Aluminum Compounds	0	0	Good
Barium Salts	Barium Compounds	0	0	Good
Benzyl Alcohol	Hydroxyl Compounds	1	1	Fair
Boric Acid	Inorganic Acids	0	0	Good
Butanol	Hydroxyl Compounds	0	0	Good
Calcium Chlorite	Calcium Compounds	0	0	Good
Carbon Disulfide	Sulfur Compounds	1	0	Fair
Cupric Chloride	Copper Compounds	0	0	Good
Cyclohexanone	Ketones	1	2	NR
Dichloromethane	Halogen Compounds	2	2	NR
Diethylamine	Aliphatic Amines	1	1	Fair
Diethylformamide	Aliphatic Amines	2	2	NR
Ethyl Acetate	Carboxylic Esters	1	0	Fair
Formaldehyde	Aliphatic Aldehydes	0	0	Good
Gasoline	Aromatic Hydrocarbons	0	0	Good
Glycol Ether	Ethers	0	0	Good
Hexane	Aliphatic Hydrocarbons	0	0	Good
Hydrochloric Acid (37%)	Inorganic Compounds	0	2	NR
Hydrogen Peroxide (30%)	Peroxides	1	0	Fair
Hydrofluoric Acid (48%)	Inorganic Acids	0	2	NR
Jet Fuel (JP-5)	Aliphatic Hydrocarbons	0	0	Good
Methanol	Aliphatic Hydroxylic Compounds	0	0	Good
Methyl Ethyl Ketone	Aliphatic Ketones	2	0	NR
Mineral Oil	Aliphatic and Alicyclic Hydrocarbons	0	0	Good
Naphtha	Hydrocarbons	0	0	Good
Nitrobenzene	Nitro Compounds	0	2	NR
Phenol	Aromatic Hydroxylic Compounds	0	2	NR
Propylene Glycol	Hydroxylic Compounds	0	0	Good
Sodium Hydroxide (50%)	Inorganic Bases	0	0	Good
Sulfuric Acid (98%)	Inorganic Acids	0	2	NR
Sulfuric Acid (50%)	Inorganic Acids	0	2	NR
Tetrachloroethylene	Halogen Compounds (Vinyl Halides)	0	0	Good
Tetrahydrofuran	Alicyclic Ethers	2	2	NR
Toluene	Aromatic Hydrocarbons	1	0	Fair
1, 1, 1-Trichloroethane	Aliphatic Halogen Compounds	1	0	Fair
Trichloroethylene	Halogen Compounds (Vinyl Halides)	1	0	Fair
Triethylamine	Aliphatic Amines	0	0	Good
Turpentine	Hydrocarbons	0	0	Good
Water	Misc	0	0	Good

Key

Swelling	Degradation	Ratings
Visually rated 0-2	Visually rated from 0-2	NR (Not Recommended)
0=none	0=none	Significant degradation or swelling
1=slight	1=slight	Fair: Slight swelling
2= significant	2= significant	Good: No Swelling

Important user notice for both the polyurethane & polyethylene chemical compatibility guides

The data contained herein is a compilation of existing published data from leading manufacturers of polyurethane and does not represent actual testing performed by stormwaterworks.com, LLC

This listing is offered only as a guide and utilizes information which, to the best of our knowledge is accurate and reliable. Due to variables and conditions of application beyond the control of stormwaterworks.com, LLC, none of the data shown in this guide is to be construed as a guarantee, expressed or implied. Stormwaterworks.com, LLC assumes no responsibility, obligation or liability in conjunction with the use or misuse of the information herein.